


## PRODUCT

**RANGE TRANSFIX**

**REFERENCE : AT E109/75 PA90**

## DESCRIPTION



**RELEASE LINER: Silicone-coated paper 90g/m<sup>2</sup>**

**ADHESIVE: Acrylic emulsion adhesive 75g/m<sup>2</sup>**

## APPLICATIONS FIELDS



- **Ideal for bonding PU foams, bitumen, heavy layers, felts and plastics : ABS, PVC, PC, PA**
- **E109 adhesive ensures good adhesion and cohesion properties.**
- **E109 adhesive is a versatile product suitable for a wide range of applications.**



## TECHNICAL DATA

	TYPICAL VALUES	TEST METHOD
<b>Peel adhesion on steel</b>		
Dwell time 24h - 180°	24 N / inch	Afera 5001
<b>Peel adhesion on PP</b>		
Dwell time 24h - 180°	18 N / inch	Afera 5001
Loop Tack	21 N / inch	Finat 9
Temperature shear resistance	75°C	SAFT
Application min Temperature	+5°C	
Continuous service Temperature	-30°C to 120°C	
Short Pick	+140°C	

## RECOMMENDATIONS

Surfaces to which adhesive is applied must be clean, dry and free of dust, release agent, grease and oil.

Certain substrates contain oils or plasticizers which may deteriorate the performance of the adhesive. This is why in some cases it is advisable to perform an ageing test in a climate chamber which will help to assess this risk.

## STORAGE

The shelf life is 9 months, when stored in its original packaging, out of direct sunlight, at temperature between +5°C and +35°C. Once removed from its packaging, the product should be protected against dust, impurities and insects.

## STANDARD PACKAGING

Standard log length : 200/250/500 meters.

Standard width : 1000/1250/1500/2000 mm.

Other possibilities out of standard are possible upon request.

## REMARKS

The above mentioned product could be used for a wide range of various applications.

We recommend to all purchasers to determine carefully, prior to use, the suitability of our product for their specific purposes. They shall assure by their own tests the compatibility with each intended use. Information supplied is accurate to the best of Adesia knowledge and is based upon all current date available to it. Properties quoted are typical and do not therefore constitute a specification.



Product datasheet AT E109/75 PA90,  
Modification Date : 04/01/2019



243 rue de Chavanne - ZAC de Chavanne - 69400 Arnas  
Tél. : +33 (0)4 74 68 22 55 - Fax : +33 (0)4 74 68 71 00  
[contact@adesia.com](mailto:contact@adesia.com) - [www.adesia.com](http://www.adesia.com)