

PRODUCT

RANGE TRANSFIX

REFERENCE : AT S911/150 PP

DESCRIPTION



RELEASE LINER: Silicone-coated polypropylene 60 μ

ADHESIVE: Acrylic solution adhesive 150g/m²

APPLICATIONS FIELDS



- **The S911 is a solution adhesive with very high cohesion.**
- **Excellent resistance to UV and humidity.**
- **Assures good conformability to flat or curved surfaces.**
- **Very good temperature shear resistance.**
- **Excellent resistance to ageing.**
- **Good plasticizer resistance**



TECHNICAL DATA

	TYPICAL VALUES	TEST METHOD
Peel adhesion on steel		
Dwell time 24h - 180°	25 N / inch	Afera 5001
Peel adhesion on PP		
Dwell time 24h - 180°	10 N / inch	Afera 5001
Loop Tack	20 N / inch	Finat 9
Temperature shear resistance	105°C	SAFT
Application min Temperature	+10°C	
Continuous service Temperature	-30°C to +150°C	
Short Pick	+170°C	

RECOMMENDATIONS

Surfaces to which adhesive is applied must be clean, dry and free of dust, release agent, grease and oil.

Certain substrates contain oils or plasticizers which may deteriorate the performance of the adhesive. This is why in some cases it is advisable to perform an ageing test in a climate chamber which will help to assess this risk.

STORAGE

The shelf life is 6 months, when stored in its original packaging, out of direct sunlight, at temperature between +5°C and +35°C. Once removed from its packaging, the product should be protected against dust, impurities and insects.

STANDARD PACKAGING

Standard log length : 200/250/300 meters.

Standard width : 2000 mm.

Other possibilities out of standard are possible upon request.

REMARKS

The above mentioned product could be used for a wide range of various applications.

We recommend to all purchasers to determine carefully, prior to use, the suitability of our product for their specific purposes. They shall assure by their own tests the compatibility with each intended use. Information supplied is accurate to the best of Adesia knowledge and is based upon all current date available to it. Properties quoted are typical and do not therefore constitute a specification.



Product datasheet AT S911/150 PP,
Modification Date : 04/30/2021



243 rue de Chavanne - ZAC de Chavanne - 69400 Arnas
Tél. : +33 (0)4 74 68 22 55 - Fax : +33 (0)4 74 68 71 00
contact@adesia.com - www.adesia.com